

SCHNEIDER LABORATORIES

INCORPORATED

2512 W. Cary Street • Richmond, Virginia • 23220-5117
804-353-6778 • 800-785-LABS (5227) • (FAX) 804-359-1475

Excellence in Service and Technology

AIHA/ELLAP 100527, NVLAP 101150-0, NYELAP/NELAC 11413, CAELAP 2078, NC 593, SC 93003

LABORATORY ANALYSIS REPORT

Lead Analysis based on EPA 7420 Method

Using SLI P26 A14

ACCOUNT #:
CLIENT:
ADDRESS:

DATE COLLECTED: 8/14/2008
DATE RECEIVED: 8/19/2008
DATE ANALYZED: 8/26/2008
DATE REPORTED: 8/26/2008

PROJECT NAME:
JOB LOCATION:
PROJECT NO.:
PO NO.:

Sample Type: PAINT

SLI Sample No.	Client Sample No.	Sample Description	Sample Wt (mg)	Total Lead (μg)*	Lead Conc (% by wt)	Lead Conc PPM
29859456	SM-1		296	32.1	0.011	109
29859457	SM-2		285	259.0	0.091	909

Analysis Run ID: 42167

Analyst:

Total Number of Pages in Report: 1

Results relate only to samples as received by the laboratory.

Reviewed By

Visit www.slabin.com for current certifications.

*Minimum Reporting Limit: 20.0 μg . Lead Based Paint contains 0.5% lead by weight per Federal statute. The OSHA Lead in Construction Standard, 29 CFR 1926.62, is invoked if any lead is present in the sample. Lead-free paint is defined as <0.06% by weight (CPSC). *Data precision justifies 2 significant figures. All internal QC parameters were met. Unusual sample conditions, if any, are described.*